

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (original): A gas barrier film having an inorganic coating layer formed by the sol-gel method or an organic-inorganic hybrid coating layer formed by the sol-gel method on a transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower.

2. (original): The gas barrier film according to claim 1 having an organic-inorganic hybrid coating layer formed by the sol-gel method on a transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower.

3. (original): The gas barrier film according to claim 1 having an inorganic coating layer formed by the sol-gel method and an organic-inorganic hybrid coating layer formed by the sol-gel method on a transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower.

4. (original): The gas barrier film according to claim 1 having an inorganic thin film layer and an organic-inorganic hybrid coating layer formed by the sol-gel method on a

transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower.

5. (original): The gas barrier film according to claim 4, wherein the inorganic thin film layer is an inorganic coating layer formed by the sol-gel method.

6. (original): The gas barrier film according to claim 1, wherein the base film has a glass transition temperature of 120°C or higher.

7. (original): The gas barrier film according to claim 1, wherein the base film has a glass transition temperature of 150°C or higher.

8. (original): The gas barrier film according to claim 1, wherein the base film has a linear thermal expansion coefficient of 20 ppm/°C or lower.

9. (original): The gas barrier film according to claim 1, wherein the base film is made of a material selected from the group consisting of polyethylene naphthalate, polycarbonate, cycloolefin polymer, polyalylate and polyethersulfone.

10. (original): The gas barrier film according to claim 1, wherein the base film contains an inorganic layered compound.

11. (original): The gas barrier film according to claim 10, wherein the weight ratio of the inorganic layered compound and a resin contained in the base film is preferably 1/100 to 100/20.

12. (original): The gas barrier film according to claim 10, wherein the inorganic layered compound contains an organic cation.

13. (original): The gas barrier film according to claim 12, wherein the organic cation contains alkylammonium ions containing a long-chain alkyl group.

14. (original): The gas barrier film according to claim 12, wherein the organic cation is contained in an amount of 0.05 to 3 equivalents relative to the cation exchange capacity of the inorganic layered compound.

15. (currently amended): 15. The gas barrier film according to claim 12, ~~wherein the base film has a laminated structure of~~ having an inorganic thin film layer and organic-inorganic hybrid coating layer formed by the sol-gel method on the base film.

16. (original): A substrate for a display having the gas barrier film according to Claim 1.

17. (original): A display device having the gas barrier film according to claim 1.

18. (original): An organic electroluminescent device having the gas barrier film according to claim 1.

19. (original): A liquid crystal device having the gas barrier film according to claim 1.

20. (withdrawn): A method for preparing a gas barrier film having an inorganic coating layer or an organic-inorganic hybrid coating layer on a transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower, which comprises the step of forming the inorganic coating layer on the transparent base film by hydrolizing and polycondensating a metal alkoxide, or the step of forming the organic-inorganic hybrid coating layer on the transparent base film by hydrolizing and polycondensating a metal alkoxide in the presence of a resin.

21. (withdrawn): A method for preparing a gas barrier film having an inorganic coating layer and an organic-inorganic hybrid coating layer on a transparent base film having a glass transition temperature of 100°C or higher and a linear thermal expansion coefficient of 40 ppm/°C or lower, which comprises the step of forming the inorganic coating layer on the transparent base film by hydrolizing and polycondensating a metal alkoxide, and the step of forming the organic-inorganic hybrid coating layer on the transparent base film by hydrolizing and polycondensating a metal alkoxide in the presence of a resin.